

SINTERING-DATA-SHEET

DR. FRITSCH GmbH & Co. KG

Dieselstraße 8

70736 Fellbach

Tel. 0711-518320; Fax 0711-5183210

powder - code:	Diaweld-3200
-----------------------	--------------

main component:	Fe	binder:	2 % alcohol	date:	23.01.2017
machine type:	DSP-25	aver. Grain size		testperson:	OE
utilisation:	Weldable backing				

heating by	die:	X	temperature measure-	pyroscope:	
	punches:		ment by:	thermocouple:	X


temperature:	$^{\circ}\text{C}$	700	740	780	820	860	900	940	
specific pressure:	N/mm^2	35	==>						
sintering time:	min	3	==>						

bending strength:	N/mm^2								
stretch at break:	%								
average hardness:	HRB	57	60	59	56	58	63	64	
hardness scattering:	HRB	56-57	60-61	57-60	54-60	55-61	63-64	64-65	
average hardness:	HRC								
hardness scattering:	HRC								
weight:	g	17	==>						
weight after sintering:	g								

Volume ($V = G_s - G_w$)	cm^3								
Density ($D = G_s / V$)	g/cm^3	7,26	7,36	7,52	7,51	7,59	7,64	7,62	

weight loss ($G = G_e - G_s$)	g								
rel. Weight loss ($Gr = G * 100$)	%							9,34	

notes:									
								extrusion	



Attention:

Depending on mould-geometry and type and place of temperature-measurement an increase up to 60 °C must be done to get the same result ! In case of moulds with a high number of graphite punches a certain friction value needs to be considered. To obtain the detailed formula you are welcome to contact us.

Property of Dr. Fritsch GmbH & Co.KG. Transmission only allowed in explicit agreement with the management.