

SINTERING - DATA - SHEET

DR. FRITSCH GmbH & Co. KG

Dieselstraße 8

70736 Fellbach

Tel. 0711-518320; Fax 0711-5183210

powder - code:	Neoloy-7150
-----------------------	-------------

main component:	Fe, Co, Cu	binder:	2 % alcohol	date:	14.06.2018
machine type:	DSP-25	aver. Grain size		testperson:	GK
utilisation:					

heating by	die:	X	temperature measurement by:	pyroscope:	
	punches:			thermocouple:	X


temperature:	°C	660	700	740	780	820	860	900	940
specific pressure:	N/mm ²	35	==>						
sintering time:	min	3	==>						

bending strength:	N/mm ²								
stretch at break:	%								
average hardness:	HRB	95	105	106	106	107	106	106	105
hardness scattering:	HRB	93-97	104-106	105-108	106-107	106-107	106-106	106-106	105-106
average hardness:	HRC								
hardness scattering:	HRC								
weight:	g	17	==>						
weight after sintering:	g								

Volume ($V = G_s - G_w$)	cm ³								
Density ($D = G_s / V$)	g/cm ³	7,54	7,82	7,88	7,94	7,97	7,97	7,96	7,96

weight loss ($G = G_e - G_s$)	g								
rel. Weight loss ($Gr = G * 10$)	%								

notes:									
---------------	--	--	--	--	--	--	--	--	--



Attention:

Depending on mould-geometry and type and place of temperature-measurement an increase up to 60 °C must be done to get the same result !
 In case of moulds with a high number of graphite punches a certain friction value needs to be considered. To obtain the detailed formula you are welcome to contact us.

Property of Dr. Fritsch GmbH & Co.KG. Transmission only allowed in explicit agreement with the management.